



Made in USA

## ***Clearview 75 LHA***      ***Technical Specifications IGDB ID: 1711 <sup>(1)</sup>***

ClearView 75LHA (Low Heat Absorption) film has been specifically designed to be much safer to install than other films on tinted and/or laminated glass that is frequently used in commercial buildings and residential apartment buildings. While this film does not block as much heat as the ClearView ICE 70 it does provide similar fade protection and can be installed on glass types where other films would have an unacceptable risk of causing excessive heat absorption into the glass and lead to thermal stress (glass breakage). Suitable for most glass types

Visible Light Transmission	77.0%
Visible Light Reflectance	15.0%
Ultraviolet Light Transmission	<1%
U-Value Summer	5.08
Solar Heat Gain Coefficient	0.64
Shading Coefficient	0.74
Infrared Rejection	51.0%
Solar Energy Transmission	59.0%
Solar Energy Reflectance	22.0%
Solar Energy Absorption	19.0%
Total Solar Energy Rejected	36.0%

### **Substrate**

Mitsubishi N5 Series  
Toray U60

### **Thickness**

1.5mil

### **Method of Coating**

Spectra-Select Sputter Coating

### **Hard Coat**

Patented scratch resistant coating designed to meet the most exacting performance standards.

### **Warranty**

Residential: Non-transferable Lifetime Warranty  
Commercial: 10 Years

**NOTES** (1) **IGDB** is the International Glazing Database maintained by the US Department of Energy. As a consumer protection all performance data and energy efficiency claims must be independently tested and verified before a product can be listed on the IGDB.

The Building Code of Australia requires that new buildings in Australia achieve minimum energy efficiency standards and uses the Windows Energy Rating Scheme (WERS) to rate the performance of glazing and window films. Window films must be listed on the IGDB to obtain a WERS in Australia.

\* Solar Specifications testing performed on film mounted to 3mm clear glass. Test, equipment and methods according to ASTM, ANSI and NFRC standards. Calculations performed using US Dept of Energy Lawrence Berkeley Lab's "Windows 5.2" program. Values expressed hereof are typical and for comparative purpose only. Performance data will vary with processing conditions.